



**GACODECK TOP COAT**  
**OCTOBER 2007**  
Supersedes 01/01

## **GACODECK TOP COAT**

### **WATER BASED ELASTOMERIC COATING**

**DESCRIPTION:** Gaco Western's GacoDeck Top Coat water-borne, single component elastomeric coatings are characterized by excellent hardness, strength, adhesion and water resistance.

**USAGE:** GacoDeck Top Coat is designed to maintain your GacoDeck waterproofing system. The GacoDeck Top Coat enhances an existing system by renewing color and increasing durability.

**STANDARD COLORS:** DT01 Oyster, DT02 Pewter, DT16 Shale, DT18 Adobe, DT47 Sedona, DT49 Desert.

### **APPLIED PRODUCT DATA**

**WEATHERABILITY:** Excellent color stability, gloss retention and chalk resistance.

**TENSILE:** ASTM D-412

Strength:	900 psi min. (6.21 MPa)
Elongation:	200% min.
Permanent Set at Break:	15% max.

**HARDNESS:** ASTM D-2240 90 Shore A

**TEAR RESISTANCE:** ASTM D-624 DIE C  
Lb./In. 250 min. (44.6 kg(f)/cm)

**WATER VAPOR PERMEABILITY:** ASTM E-96 0.06 Perm Inches  
Method B, 100% R.H. Difference

**TOXICITY:** We believe cured coating to be non-toxic. However, confirming tests have not been conducted.

**ADHESION:** Adheres well to most surfaces.

**PACKAGED PRODUCT DATA**

COVERAGE:	Sq. Ft./Gal./Mil		712 (17.49 m <sup>2</sup> / L / .02 mm)
SOLIDS:	Weight:	Method 4041	57.36%
		Fed. Std. 141	
	Volume:		44.4%
V.O.C. :	Volatile organic compounds content is 129 grams per liter.		
FLASH POINT:	Above 200°F (93°C). Tag Open Cup		
STORAGE:	Three years in original unopened container. Protect from freezing. Freezing temperature 29°F (-2°C). If frozen, thaw at 40 to 80°F (4°C to 27°C). If melted to a smooth, homogeneous condition, it is equal to original material. Do not allow material or surface of container to exceed 100°F (38°C). Gelation may occur.		

**APPLICATION**

GacoDeck Top Coat products are water based coatings and require the complete evaporation of water to achieve cure. DO NOT apply to surfaces that are, or will be lower than, 50°F (10°C) within 6 hours.

Clean up using GacoDeck Wash or water mixed with liquid detergent.